

Be
brilliant.

nyloprint® WS-W Digital

Steel based letterpress printing plate with improved reproduction characteristics



Product features

+ Improved reproduction characteristics

- + Steeper relief shoulders and deeper reverses
- + Higher definition / fidelity
- + Crisper edges
- + Reproduction of smallest elements on plate and print
- + Superior results in combination with LED exposure (e.g. nyloprint® NExT)

+ Efficient, reliable and fast plate processing

- + Plate processing within 25-35 min
- + Highly productive and cost efficient
- + Wide exposure latitude
- + Excellent visual check due to high colour contrast of the finished plate
- + Suitable for processing with brush and plush washers as well as for exposure with UV-A tubes of type O9N and 10R

+ Product applications

- + Ideal for tubes, cups and cans printing, security printing and label printing
- + Suitable for rotary letterpress, imprinting units and special-purpose printing presses

+ Highest print quality

- + High print contrast with an exceptional tonal range
- + Smaller halftone dots (< 20 micron) resulting in brilliant gradations and fading of vignettes
- + High resolution - up to 10 160 dpi
- + Excellent solid density due to optimised surface with brilliant ink transfer
- + Very good durability for long print runs

Advantages of nyloprint® Digital

✓ Higher print quality

- + Reproduction of finer details and less dot gain due to digital imaging
- + High dimensional stability
- + No defects caused by dust and damaged films
- + No data loss during transfer
- + Smoother plate surface can achieve higher density
- + Highly consistent especially when repeating plate processing

✓ Cost effective and environmentally friendly

- + No film costs
- + No chemicals for film development
- + Electronic filing of graphics, film storage is redundant
- + Easy and fast data exchange - worldwide

XSYS

Print solid. Stay flexible.

nyloprint® WS-W Digital

nyloprint® WS-W Digital

	73	83	94
Technical characteristics¹			
Base material	steel		
Colour of raw plate	red		
Total thickness (mm) (inch)	0.73 0.029"	0.83 0.033"	0.94 0.037"
Plate hardness (Shore D)	77	76	73
Relief depth (mm) (inch)	0.46 0.018"	0.56 0.022"	0.67 0.026"
Tonal range (%) at screen ruling	1-98 60 l/cm (150 lpi)		
Fine line width (down to µm)	<100	<100	<100
Isolated dot diameter (down to µm)	<200	<200	<200
Distortion factor (mm) (inch)	3.85 0.152"	4.49 0.177"	5.19 0.204"

Processing parameters¹

Main exposure (min)	1.0-3.5
Washout at 30°C / 86° F (min)	2.0-3.5
Drying time at 80°C / 176°F (min)	10-15
Post exposure (min)	2

Processing Equipment

Suitable equipment	nyloprint® WS-W Digital plates can be processed with nyloprint® processing equipment and all similar devices and be used with all laser systems suitable for imaging letterpress plates.
Printing inks and varnishes	Suitable for UV and oil based inks and varnishes.
Washout medium	For washout only tap water is needed.
Processing information	A detailed description of the individual platemaking steps, as well as detailed information about processing and storing can be found in the nyloprint® User Guide.
High quality standard	nyloprint® printing plates are manufactured according to DIN ISO 9001, DIN ISO 14001 and DIN ISO 50001 standards and requirements. This process guarantees our customers consistent high quality products and services.

¹) All processing parameters and technical specifications depend on, among others, the processing equipment and lamp age. The above mentioned processing parameters were established under optimum conditions on nyloprint® processing equipment. Under other conditions the processing times can differ. Therefore the above mentioned values are only to be used as a guide.

Please contact us for additional information.

info@xsyglobal.com • www.xsyglobal.com

The aim of our technical documents is to inform and advise our customers. The information provided herein is correct to the best of XSYS's knowledge. No liability for any errors, facts or opinions is accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted. Product names followed by ® are trademarks registered by XSYS Germany GmbH and/or its affiliates.



XSYS
Print solid. Stay flexible.